



## processing advices for sewing tapes with fixative coating



Please take notice of the following recommended temperatures:

<b>steam – ironing table</b> (iron with Teflon-sole)	200°C with steam (3 points)	even ironing movement with slight pressure (about 8 sec.)
<b>common iron</b>	110-160°C with steam (2-3 points)	even ironing movement with slight pressure (about 10 sec.) choose the temperature according to the softness of the fabric
	160-200°C without steam (2-3 points)	cover the fabric with a wet cotton cloth, even ironing movement with slight pressure (about 10-15 sec.)

Further processing tips:

- Never iron the fixing coated tape directly **defilements on the Teflon-sole!!!**
- In case of processing very thin fabrics please protect the ironing table from single off coming parts of the coating by putting a cloth on it.
- For the optimum result we recommend to make an ironing test with the fabric you would like to use.
- washing directions: 40°C gentle wash  
(put it in the washing machine either slightly rolled in a washing bag or, if it is an eyelet decoration, slightly tied)  
Keep the mechanical movements during the washing as less as possible

Single parts of the fixing coating that unglue during the washing, can be shaken off or brushed off easily and do not reduce the quality of the tapes.

Ruther & Einkenkel GmbH & Co.KG, Annenstraße 5, 09456 Annaberg-Buchholz  
Telefon: 03733/1408-0 | Fax: 03733/1408-20  
www.ruther-einkenkel.de | info@ruther-einkenkel.de



## processing advices for sewing tapes with fixative coating



Please take notice of the following recommended temperatures:

<b>steam – ironing table</b> (iron with Teflon-sole)	200°C with steam (3 points)	even ironing movement with slight pressure (about 8 sec.)
<b>common iron</b>	110-160°C with steam (2-3 points)	even ironing movement with slight pressure (about 10 sec.) choose the temperature according to the softness of the fabric
	160-200°C without steam (2-3 points)	cover the fabric with a wet cotton cloth, even ironing movement with slight pressure (about 10-15 sec.)

Further processing tips:

- Never iron the fixing coated tape directly **defilements on the Teflon-sole!!!**
- In case of processing very thin fabrics please protect the ironing table from single off coming parts of the coating by putting a cloth on it.
- For the optimum result we recommend to make an ironing test with the fabric you would like to use.
- washing directions: 40°C gentle wash  
(put it in the washing machine either slightly rolled in a washing bag or, if it is an eyelet decoration, slightly tied)  
Keep the mechanical movements during the washing as less as possible

Single parts of the fixing coating that unglue during the washing, can be shaken off or brushed off easily and do not reduce the quality of the tapes.

Ruther & Einkenkel GmbH & Co.KG, Annenstraße 5, 09456 Annaberg-Buchholz  
Telefon: 03733/1408-0 | Fax: 03733/1408-20  
www.ruther-einkenkel.de | info@ruther-einkenkel.de

